

Application No. 10/591,455
Reply to Office Action of June 24, 2008

IN THE SPECIFICATION

Please replace Table 3 on page 37 with the attached Table 3.

[0077]

Table 3

	Comp.Ex.1	Comp.Ex.9	Comp.Ex.10	Comp.Ex.11	Comp.Ex.12	Comp.Ex.13
Polylactic acid polymer (A)	100	50	50	25	50	50
acrylic polymer (B)	-	50	50	75	50	50
Graft copolymer (C)	S-2005	-	-	-	-	-
	S-2001	-	-	15	-	-
	SRK-200	-	-	-	-	-
	W-450A	-	-	-	-	-
	FM-50	-	-	-	-	-
	IM-808	-	-	-	-	-
	KM-355P	-	-	-	-	-
	M-1	-	-	-	-	-
	C-102	-	-	-	15	-
	C-223	-	-	-	-	15
Biodegradable reinforcing agent	-	-	15	-	-	-
Charpy impact strength (KJ/m ²)	23.4	2.1	2.2	5.7	1.9	22.2
Total light transmission (%)	70.3	92.7	91.1	52.2	36.4	35.5
Haze (%)	44.0	5.4	7.6	88.0	87.6	89.5
Deflection temperature under load (°C)	52.6	64.4	60.7	74.5	62.7	62.3
Rab	1.449	1.469	1.469	1.48	1.469	1.469
Rc	1.464	-	-	1.469	1.514	1.51
Rc - Rab	0.015	-	-	$\frac{-0.011}{-0.001}$	0.045	0.041